



Product Data and Specification

Seralon M36

Technical Data

Raw Material	Staple Spun Polyester
Construction	3 Ply
Linear Density (D'tex)	958
Tensile Strength (N)	35.6
Elongation at Break (%)	20.3
Recommended Needle Size (Nm)	100 - 130

Product Description and Make-up

Code	Description	Sales Unit
A418	Seralon M36/3800M K/Spool 	Individually or 5 units per box

Fields of Application

<ol style="list-style-type: none">1. General seaming of heavy weight fabrics2. Decorative top stitching
--

Contact Details

Telephone: Sales +27 21 981 3600	Email: orders@acagroup.co.za
Telephone: Admin +27 21 981 1133	Web: http://www.acathreads.co.za

ISO 9001: 2008



Made in SA



SABS Mark Bearing

